

## SHIELDING PAINT TEST REPORT

Client	Block Radiation Limited Bank Top, Kiln Lane, Paythorne, BB7 4JD, UK 0044-(0)1200 44 54 75
Contractor	Grabmann Elektrotechnik, Building Biology, Environmental Analysis A-4362 Bad Kreuzen 100, Bad Kreuzen 52, Austria, EU
Product	Blocpaint – EMF shielding paint
Order	Testing of shielding power of shielding paint
Date	13.02.2013
Device under test	Preparation of test plate by contractor 1) drywall / gypsum plaster board 2) primer / base coat: Blocpaint Basecoat 3) shielding paint coat: Blocpaint shielding paint in single layer application; 207 gramms per m <sup>2</sup> ~ 6 m <sup>2</sup> per liter coverage
Test results	Shielding performance: from 800 mhz to 6 ghz > 30 dB => 99,9% reduction of radiation

